

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application.

Listing of Claims:

1. (currently amended) A method of incorporating a UV inhibitor into a polyester resin, the method comprising:

a) forming a reaction mixture substantially free of a titanium containing ester exchange catalyst compound and comprising:

a diol,


a diacid component selected from the group consisting of dicarboxylic acids, dicarboxylic acid derivatives, and mixtures thereof,

an antimony containing compound in an amount of less than 0.1% of the total weight of the reaction mixture,

a phosphorus containing compound present in an amount of less than about 0.1% of the total weight of the reaction mixture,

a metal containing compound selected from the group consisting of zinc containing compounds, and manganese containing compounds, present in an amount from about 10 ppm to about 300 ppm, and

a UV inhibitor having formula I:



wherein,

R is hydrogen, alkyl, substituted alkyl, aryl, substituted aryl, cycloalkyl, substituted cycloalkyl, or alkenyl;

R¹ is hydrogen, or alkyl, aryl, or cycloalkyl, all of which may be substituted;

R² is hydrogen or any radical which does not interfere with condensation with the polyester;

R³ is hydrogen or 1-3 substituents selected from alkyl, substituted alkyl, alkoxy, substituted alkoxy, and halogen;


P is cyano or a group selected from carbamyl, aryl, alkylsulfonyl, arylsulfonyl, heterocyclic, alkanoyl or aroyl, all of which groups may be substituted; and

b) polymerizing the reaction mixture in a polycondensation reaction system, the polycondensation reaction system having a first reaction chamber, a last reaction chamber, and one or more intermediate reaction chambers between the first reaction chamber and the last reaction chamber, wherein the reaction system is operated in series such that the reaction mixture is progressively polymerized in the first reaction chamber, the one or more intermediate reactions, and the last reaction chamber.


2. (currently amended) The method of claim 1 wherein:

R² is hydrogen, alkyl, aralkyl, cycloalkyl, cyanoalkyl, aryl, alkoxyalkyl or hydroxyalkyl;



R is selected from hydrogen; cycloalkyl; cycloalkyl substituted with one or two of alkyl, alkoxy or halogen; phenyl; phenyl substituted with 1-3 of alkyl, alkoxy, halogen, alkanoylamino, or cyano; straight or branched lower alkenyl; straight or branched alkyl and such alkyl substituted with 1-3 of the following: halogen; cyano; succinimido; glutarimido; phthalimido; phthalimidino; 2-pyrrolidono; cyclohexyl; phenyl; phenyl substituted with alkyl, alkoxy, halogen, cyano, or alkylsulfamoyl; vinylsulfonyl; acrylamido; sulfamyl; benzoylsulfonicimido; alkylsulfonamido; phenylsulfonamido; alkenylcarbonylamino; groups of the formula



wherein Y is -NH-,




-O-, -S-, or -CH₂O-; -S-R⁴ ; SO₂CH₂CH₂SR⁴ ; wherein R⁴ is alkyl, phenyl, phenyl substituted with halogen, alkyl, alkoxy, alkanoylamino, or cyano, pyridyl, pyrimidinyl, benzoxazolyl, benzimidazolyl, benzothiazolyl, or a radical of the formulae



-NHXR⁵ ; -CONR⁶R⁶ ; and -SO₂NR⁶R⁶; wherein R⁶ is selected from H, aryl, alkyl, and alkyl substituted with halogen, phenoxy, aryl, -CN, cycloalkyl, alkylsulfonyl, alkylthio, or alkoxy; X is -CO-, -COO-, or -SO₂ -; R⁵ is selected from alkyl and alkyl substituted with halogen, phenoxy, aryl, cyano, cycloalkyl, alkylsulfonyl, alkylthio, and alkoxy; and when X is -CO-, R⁵ also can be hydrogen, amino, alkenyl, alkylamino, dialkylamino, arylamino, aryl, or furyl; alkoxy; alkoxy substituted with cyano or alkoxy; phenoxy; or phenoxy substituted with 1-3 of alkyl, alkoxy, or halogen; and

P is cyano, carbamyl, N-alkylcarbamyl, N-alkyl-N-arylcarbamyl, N,N-dialkylcarbamyl, N,N-alkyl-arylcarbamyl, N-arylcarbamyl, N-cyclohexylcarbamyl, aryl, 2-benzoxazolyl, 2-benzothiazolyl, 2-benzimidazolyl, 1,3,4-thiadiazol-2-yl, 1,3,4-oxadiazol-2-yl, alkylsulfonyl, arylsulfonyl, alkanoyl or aroyl.

3. (original) The method of claim 1 wherein R^1 is hydrogen.
4. (original) The method of claim 1 wherein P is cyano.
5. (original) The method of claim 1 wherein R^1 is hydrogen and P is cyano.
6. (original) The method of claim 1 wherein the UV inhibitor is a compound having formula II:



7. (original) The method of claim 1 wherein the reaction mixture contains from 0.0 to 2 ppm titanium metal.
8. (currently amended) The method of claim 1 wherein the polymerization is carried out with each reaction chamber having a reaction pressure such that the reaction pressure in the first chamber is from about 20 to 50 psi and the reaction pressure in the last reaction chamber is from about 0.1 mm Hg to about 2 mm Hg with the reaction pressure in each of the one or more intermediate reactor being between 50 psi and 0.1 mm Hg.

9. (original) The method of claim 1 wherein the reaction mixture contains 0.0 ppm titanium metal.

10. (original) The method of claim 1 wherein the diol component is selected from the group consisting of ethylene glycol, 1,4-cyclohexanedimethanol, 1,2-propanediol, 1,3-propanediol, 1,4-butanediol, 2,2-dimethyl-1,3-propanediol, 1,6-hexanediol, 1,2-cyclohexanediol, 1,4-cyclohexanediol, 1,2-cyclohexanedimethanol, 1,3-cyclohexanedimethanol, X,8-bis(hydroxymethyl)tricyclo-[5.2.1.0]-decane wherein X represents 3, 4, or 5; diols containing one or more oxygen atoms in a chain and mixtures thereof.

11. (original) The method of claim 1 wherein the diacid component comprises a component selected from the groups consisting of terephthalic acid, isophthalic acid, naphthalene dicarboxylic acid, 1,4-cyclohexanedicarboxylic acid, 1,3-cyclohexanedicarboxylic acid, succinic acid, glutaric acid, adipic acid, sebacic acid, 1,12-dodecanedioic acid, and esters thereof; and mixtures thereof.

12. (original) The method of claim 11 wherein the diacid component comprises dimethyl terephthalate.

13. (original) The method of claim 11 wherein the molar ratio of the diol component to the diacid component is from about 0.5 to about 4.

14. (original) The method of claim 1 wherein the reaction mixture further comprises a component containing a metal selected from the group consisting of zinc, manganese, and mixtures thereof, an antimony containing component, and a phosphorus containing component.

15. (original) The method of claim 14 wherein the metal containing component is zinc acetate or manganese acetate, the antimony containing component is antimony trioxide, and the phosphorus containing component is phosphoric acid.

16. (original) The method of claim 15 wherein the metal containing component is zinc acetate present in an amount from about 10 to about 200 ppm.

17. (original) The method of claim 15 wherein the antimony trioxide is present in an amount from about 20 to about 500 ppm.

18. (original) The method of claim 15 wherein the phosphoric acid is present in an amount from about 5 to about 200 ppm.

19. (currently amended) The method of claim 14 further comprising ~~wherein~~ one or more components selected from the group consisting of an iron containing compound, a toner, a cobalt containing compound, and mixtures thereof.

20-58. (Canceled)